



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 315 481 B1**

12

EUROPEAN PATENT SPECIFICATION

45 Date of publication of patent specification: **18.05.94** 51 Int. Cl.⁵: **C08L 23/06**

21 Application number: **88310417.6**

22 Date of filing: **04.11.88**

54 **Olefin resin composition for injection molding.**

30 Priority: **05.11.87 JP 278350/87**
05.11.87 JP 278351/87
15.12.87 JP 316902/87
15.12.87 JP 316903/87

43 Date of publication of application:
10.05.89 Bulletin 89/19

45 Publication of the grant of the patent:
18.05.94 Bulletin 94/20

64 Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

56 References cited:
EP-A- 0 134 427
EP-A- 0 274 536
GB-A- 2 028 845
US-A- 4 281 070

73 Proprietor: **mitsui petrochemical industries, LTD.**
2-5, Kasumigaseki 3-chome
Chiyoda-ku
Tokyo 100(JP)

72 Inventor: **Shiraki, Takeshi**
2-7, Waki 5-chome
Waki-cho
Kuga-gun Yamaguchi-ken(JP)
Inventor: **Muraoka, Kyouji**
1085, Nishimigama
Ohshima-cho
Ohshima-gun Yamaguchi-ken(JP)
Inventor: **Hiroshige, Kunie**
3-18 Aoki-cho 2-chome
Iwakuni-shi Yamaguchi-ken(JP)

74 Representative: **Cresswell, Thomas Anthony**
et al
J.A. KEMP & CO.
14 South Square
Gray's Inn
London WC1R 5LX (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 315 481 B1

DescriptionBackground of the Invention

(1) Field of the Invention

The present invention relates to an olefin resin composition for injection molding. More particularly, the present invention relates to an olefin resin composition for injection molding, which comprises an ultra-high-molecular-weight polyethylene, can be injection-molded and has excellent sliding characteristics, excellent abrasion resistance, improved heat resistance and improved rigidity in combination.

(2) Description of the Related Art

Ultra-high-molecular-weight polyethylene is excellent in impact strength, abrasion resistance, chemical resistance and tensile strength over general-purpose polyethylene and the application field of ultra-high-molecular-weight polyethylene as an engineering plastic material is being expanded. However, ultra-high-molecular-weight polyethylene has a much higher melt viscosity and a lower flowability than general-purpose polyethylene, and therefore, molding of ultra-high-molecular-weight polyethylene by ordinary extrusion molding or injection molding is very difficult. Accordingly, ultra-high-molecular-weight polyethylene is practically molded by compression molding, and on rare occasions, the polymer is molded into rods or the like at a low speed by extrusion molding.

If ultra-high-molecular-weight polyethylene inferior in the melt flowability is molded by injection molding, a shear fracture flow is generated while the resin is filled in a cavity of a mold and mica-like delamination is caused in the molded body, and therefore, a molded article exerting excellent characteristics of ultra-high-molecular-weight polyethylene cannot be obtained. Namely, the molded article is inferior to a molded article of general-purpose polyethylene.

As the injection molding method in which delamination is not caused, we previously proposed a method in which before injection molding of the resin or after completion of injection molding, the volume of a mold cavity is slightly increased and the mold is compressed to a predetermined volume (see Japanese Patent Publication No. 57-30067 and Japanese Patent Publication No. 60-58010). If this method is adopted, an injection-molded article having inherent excellent characteristics of ultra-high-molecular-weight polyethylene, such as high impact strength and high abrasion resistance, can be obtained without occurrence of delamination. However, an injection molding machine provided with a mechanism for changing the volume of a mold cavity should be used for carrying out injection molding according to this method, and an injection molding machine for general-purpose polyethylene cannot be directly used.

As the method for improving the melt flowability of an ultra-high-molecular-weight polyolefin, there have been proposed various methods in which an ultra-high-molecular-weight polyolefin, is mixed with a low-molecular-weight or high-molecular-weight polyolefin.

EP-A-0274536 which was not published until after the latest priority date claimed in the present application described polyolefin compositions for injection moulding which comprise superhigh and low to high molecular weight polyethylenes.

Summary of the Invention

We found that an olefin resin composition comprising ultra-high-molecular-weight polyethylene having an intrinsic viscosity of 10 to 40 dl/g as measured in decalin as the solvent at 135 °C and low-molecular-weight or high-molecular-weight polyethylene having an intrinsic viscosity lower than that of the ultra-high-molecular-weight polyethylene, in which the ultra-high-molecular-weight polyethylene is present in an amount of 15 to 40% by weight based on the sum of both of the polyethylenes, the intrinsic viscosity $[\eta]_c$ of the entire composition is 3.5 to 15 dl/g and the melt torque T of the combination of both the polyethylenes is lower than 4.5 kg.cm, can be easily molded by using a general-purpose injection molding machine without substantial decrease of excellent sliding characteristics, abrasion resistance, impact strength, chemical resistance and tensile strength inherently possessed by ultra-high-molecular-weight polyethylene, and that if a predetermined amount of an additive such as a filler is incorporated into this olefin resin composition, various properties such as heat resistance, rigidity, impact strength, self-lubricating property, abrasion resistance and moldability can be improved without substantial decrease of the most characteristic properties of the above-mentioned olefin resin composition, that is, such sliding characteristics as (1) the abrasion coefficient, (2) the dynamic friction coefficient and (3) the critical PV value.

It is therefore a primary object of the present invention to provide an ultra-high-molecular-weight polyolefin composition which can be easily injection-molded into mechanical, electric or electronic parts, for which a high precision is required, without substantial decrease of excellent mechanical properties, abrasion resistance and sliding characteristics inherently possessed by the ultra-high-molecular-weight polyolefin, and which gives a molded article improved in heat resistance, rigidity, impact strength, self-lubricating property and abrasion resistance.

Another object of the present invention is to provide a sliding material which can be easily injection-molded into a part having a high mechanical precision and gives a molded article having excellent self-lubricating property, abrasion resistance and light weight in combination.

More specifically, in accordance with the present invention, there is provided an olefin resin composition for injection molding, which comprises (A) an olefin resin composition comprising ultra-high-molecular-weight polyethylene having an intrinsic viscosity of 10 to 40 dl/g as measured in decalin as the solvent at 135°C and low-molecular-weight or high-molecular-weight polyethylene having an intrinsic viscosity lower than that of the ultra-high-molecular-weight polyethylene, in which the ultra-high-molecular-weight polyethylene is present in an amount of 15 to 40% by weight based on the sum of both of the polyethylenes and the two polyethylenes as a whole have an intrinsic viscosity $[\eta]_c$ of 3.5 to 15 dl/g and a melt torque T lower than 4.5 kg.cm, and (B) 1 to 70% by weight, based on the olefin resin composition, of an addition selected from the group consisting of fine particulate inorganic fillers, fibrous fillers and liquid and solid lubricants.

Furthermore, in accordance with the present invention, there is provided a sliding material which comprises an olefin resin composition comprising ultra-high-molecular-weight polyethylene having an intrinsic viscosity of 10 to 40 dl/g as measured in decalin as the solvent at 135°C and low-molecular-weight or high-molecular-weight polyethylene having an intrinsic viscosity lower than that of the ultra-high-molecular-weight polyethylene, in which the ultra-high-molecular-weight polyethylene is present in an amount of 15 to 40% by weight based on the sum of both of the polyethylenes and the two polyethylenes as a whole have an intrinsic viscosity $[\eta]_c$ of 3.5 to 15 dl/g and a melt torque T lower than 4.5 kg.cm, and 1 to 70% by weight, based on the olefin resin composition, of a liquid or solid lubricant.

Detailed Description of the Preferred Embodiments

In the composition of the present invention, ultra-high-molecular-weight polyethylene has excellent sliding characteristics such as a low abrasion coefficient, a low dynamic friction coefficient and a large critical PV value and is excellent in impact strength, tensile strength and chemical resistance, and therefore, ultra-high-molecular-weight polyethylene is an indispensable component. It is important that this ultra-high-molecular-weight polyethylene should have an intrinsic viscosity $[\eta]_u$, as measured in decalin as the solvent (the intrinsic viscosity referred to herein is one determined according to this method), of 10 to 40 dl/g, especially 15 to 35 dl/g. If $[\eta]_u$ is too low and below the above-mentioned range, the sliding characteristics and mechanical properties are poorer than those of ultra-high-molecular-weight polyethylene having $[\eta]_u$ within the above-mentioned range. If $[\eta]_u$ exceeds the above-mentioned range, even though the ultra-high-molecular-weight polyethylene is combined with a component described hereinafter, the injection moldability is degraded, and in the obtained molded article, the appearance is degraded and a flow mark or the like is formed, and laminar peeling is readily caused and abrasion resistance characteristics are degraded.

Low-molecular-weight or high-molecular-weight polyethylene having an intrinsic viscosity lower than that of the ultra-high-molecular-weight polyethylene, which is used in the present invention, is an indispensable component for imparting an injection moldability to the ultra-high-molecular-weight polyethylene. In order to maintain the intrinsic viscosity and melt torque of the composition as a whole within the ranges specified in the present invention, it is preferred that the intrinsic viscosity $[\eta]_h$, as determined according to the method described in detail hereinafter, be 0.1 to 5 dl/g, especially 0.5 to 3 dl/g. If $[\eta]_h$ is too low and below the above-mentioned range, bleeding or other defect appears on the surface of the molded article, and if $[\eta]_h$ exceeds the above-mentioned range, the melt flowability is degraded and the moldability of the composition as a whole tends to be degraded.

If the ultra-high-molecular-weight polyethylene is combined with the low-molecular-weight or high-molecular-weight polyethylene under specific conditions, a low friction coefficient, a low abrasion coefficient and a large critical PV value can be imparted to the composition while imparting an excellent injection moldability to the composition. First of all, the ultra-high-molecular-weight polyethylene should be present in an amount of 15 to 40% by weight, especially 20 to 35% by weight, based on the entire olefin resin composition. If the amount of the ultra-high-molecular-weight polyethylene is too small and below the above-mentioned range, the composition is inferior in the friction coefficient and abrasion resistance to the composition comprising the ultra-high-molecular-weight polyethylene in an amount within the above-

mentioned range. If the amount of the ultra-high-molecular-weight polyethylene exceeds the above-mentioned range, the moldability is degraded and delamination is caused, resulting in reduction of the abrasion resistance.

This olefin composition as a whole should have an intrinsic viscosity $[\eta]_c$ of 3.5 to 15 dl/g, especially 5 4.0 to 10 dl/g. If $[\eta]_c$ is too low and below the above-mentioned range, the composition is inferior in the dynamic friction coefficient and abrasion resistance to the composition having $[\eta]_c$ within the above-mentioned range. If $[\eta]_c$ exceeds the above-mentioned range, both of the moldability and the abrasion resistance, due to delamination, are degraded. The melt torque T referred to in the instant specification and appended claims is a value measured at a temperature of 240 °C under a pressure of 5 kg/cm² at an 10 amplitude of $\pm 3^\circ$ and a frequency of 6 CPM by using JSR Curastometer (supplied by Imanaka Kikai Kogyo K.K.). An ordinary screw cannot transport a composition having a melt torque T higher than 4.5 kg.cm, and this composition cannot be injection-molded by a general-purpose injection molding machine. Accordingly, the melt torque T should be lower than 4.5 kg.cm.

The composition of the present invention comprises the above-mentioned olefin resin composition and, 15 incorporated therein, an additive selected from the group consisting of fine particulate inorganic fillers, fibrous fillers and liquid and solid lubricants. Namely, by incorporating the above-mentioned additive into the olefin resin composition in an amount of 1 to 70% by weight based on the olefin resin composition, the injection moldability of the composition and the heat resistance, rigidity, impact resistance, self-lubricating property and abrasion resistance of the molded article can be improved without decrease of the above- 20 mentioned characteristics inherently possessed by the olefin resin composition.

In general, in order to attain a extender effect or to improve the impact strength, heat resistance, abrasion resistance and electrically insulating property, fillers are often incorporated in molded plastic articles. In the composition of the present invention comprising an olefin resin composition comprising ultra- 25 high-molecular-weight polyethylene and low-molecular-weight or high-molecular-weight polyethylene and a fine particulate inorganic filler, the heat resistance expressed by the heat distortion temperature is sometimes increased by more than about 40 °C as composed with that of the filler-free composition and the rigidity expressed by the flexural elastic modulus is almost doubled. Moreover, such unexpected improvements of the characteristics can be attained without substantial decrease of excellent sliding characteristics inherently possessed by the olefin resin composition, such as (1) a low abrasion coefficient, (2) a low 30 dynamic friction coefficient and (3) a high critical PV value.

Furthermore, by incorporating a fine particulate inorganic filler into the specific olefin resin composition, the dimension stability of the injection-molded article is improved, and formation of defects often observed on injection-molded articles, such as so-called "sink mark" and "warpage", can be reduced, whereby the appearance characteristics and mechanical precision of the molded article can be improved. Moreover, the 35 molding cycle can be shortened. Thus, prominent advantages can be attained with respect to the moldability.

It also is important that the amount incorporated to the filler should be within the above-mentioned range. If the amount incorporated of the filler is too small and below the above-mentioned range, the degree 40 of the improvement of the heat resistance, rigidity and moldability is lower than in the molded article in which the filler is incorporated in an amount within the above-mentioned range. If the amount incorporated of the filler exceeds the above-mentioned range, the melt flowability is reduced and the injection moldability is degraded, and also the sliding characteristics of the molded article are degraded.

In the present invention, if a fibrous filler is used, the above-mentioned advantages attained by the fine 45 particulate inorganic filler are similarly attained, and furthermore, the mechanical properties such as the tensile strength are prominently improved and also the impact strength is prominently improved.

Moreover, in the present invention, if a liquid or solid lubricant is incorporated into the above-mentioned olefin resin composition, the dynamic friction coefficient and abrasion coefficient can be further reduced without degradation of excellent characteristics inherently possessed by the olefin resin composition, such 50 as excellent injection moldability, self-lubricating property, abrasion resistance, impact strength and mechanical strength.

The lubricant should be incorporated in an amount within the above-mentioned range. If the amount incorporated of the lubricant is too small and below the above-mentioned range, the effect of improving the dynamic friction coefficient or abrasion resistance is lower than the effect attained when the lubricant is incorporated in an amount within the above-mentioned range. If the amount incorporated of the lubricant 55 exceeds the above-mentioned range, the mechanical strength or elastic modulus of the sliding material degrades much as compared with the sliding material in which the lubricant is incorporated in an amount within the above-mentioned range.

The present invention will now be described in detail.

Olefin Resin Composition

Each of ultra-high-molecular-weight polyethylene and low-molecular-weight or high-molecular-weight polyethylene used in the present invention is a homopolymer of ethylene or a copolymer of ethylene as the main component with other α -olefin such as propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, decene, 1-dodecene, 4-methyl-1-pentene or 3-methyl-1-pentene.

The olefin resin composition used in the present invention can be prepared by mixing the above-mentioned ultra-high-molecular-weight polyethylene and low-molecular-weight or high-molecular-weight polyethylene at the above-mentioned mixing ratio and melt-kneading the mixture. In order to form a homogeneous composition, it is especially preferred that a multi-staged polymerization be adopted for the preparation. More specifically, an olefin composed mainly of ethylene is polymerized in the presence of a Ziegler catalyst comprising a highly active solid titanium catalyst component and an organic aluminum compound catalyst component in the absence of hydrogen to form ultra-high-molecular-weight polyethylene, and the above-mentioned olefin is polymerized in the presence of hydrogen to form low-molecular-weight or high-molecular-weight polyethylene. A highly active solid titanium catalyst component comprising magnesium, titanium and halogen as indispensable ingredients is especially preferred.

The specific Ziegler catalyst used is a catalyst of a specific state, which is formed in principle, of a solid titanium catalyst component and an organic aluminum compound catalyst component. As the solid titanium catalyst component, there is preferably used, for example, a highly active, fine powdery catalyst component having a narrow particle size distribution and an average particle size of about 0.01 to about 5 μ and comprising several fine spheres bonded to one another. The highly active, fine powdery titanium catalyst component having such a specific state can be prepared by strictly adjusting precipitation conditions when a solid product is precipitated by contacting a magnesium compound in the liquid state with a titanium compound in the liquid state, for example, in the preparation of a solid titanium catalyst component disclosed in Japanese Patent Application Laid-Open Specification No. 811/81. More specifically, in the process disclosed in the above-mentioned laid-open specification, a hydrocarbon solution containing magnesium chloride and a higher alcohol is mixed with titanium tetrachloride at a low temperature and the temperature is elevated to about 50 to about 100 °C to precipitate a solid product, and at this precipitation step of this process, a monocarboxylic acid ester is made present in a minute amount of about 0.01 to about 0.2 mole per mole of magnesium chloride and the precipitation is effected under a strong stirring. If necessary, the precipitated solid product may be washed with titanium tetrachloride. Thus, a solid catalyst component satisfactory in both of the activity and the particulate state can be obtained. In this catalyst component, for example, titanium is contained in an amount of about 1 to about 6% by weight, and the halogen/titanium atomic ratio is from about 5 to about 90 and the magnesium/titanium atomic ratio is from about 4 to about 50.

A fine sphere having a narrow particle size distribution and an average particle size of 0.01 to 5 μ , preferably 0.05 to 3 μ , which is obtained by subjecting the so-prepared solid titanium catalyst component to a shearing treatment at a high speed, can also be preferably used as the highly active, fine powdery titanium catalyst component. More specifically, for this high-speed shearing treatment, there is adopted a method in which a slurry of the solid titanium catalyst component is treated in an inert gas atmosphere for an appropriate time by using a commercially available homomixer. In this method, in order to prevent reduction of the catalytic activity, an organic aluminum compound can be added in an equimolar amount to titanium in advance. Furthermore, there can be adopted a method in which the treated slurry is filtered through a sieve to remove coarse particles. The above-mentioned highly active, fine powdery titanium catalyst component having a very fine particle size can be obtained through the foregoing methods.

As the organic aluminum compound catalyst component, there are preferably used, for example, trialkyl aluminum compounds such as triethyl aluminum and triisobutyl aluminum, dialkyl aluminum chlorides such as diethyl aluminum chloride and diisobutyl aluminum chloride, alkyl aluminum sesquichlorides such as ethyl aluminum sesquichloride, and mixtures thereof.

At the polymerization step for formation of the ultra-high-molecular-weight polyethylene, it is preferred that the highly active titanium catalyst component (A) be used in an amount of about 0.001 to about 20 milligram-atoms, especially about 0.005 to about 10 milligram-atoms, as the titanium atom per liter of the medium, and the organic aluminum compound catalyst component (B) be used in an amount corresponding to an Al/Ti atomic ratio of from about 0.1 to about 1000, especially from about 1 to about 500. The temperature adopted at the polymerization step for formation of the ultra-high-molecular-weight polyethylene is ordinarily about -20 to about 120 °C and preferably about 0 to about 100 °C. It is especially preferred that this temperature be about 5 to about 95 °C. The pressure adopted for the polymerization is a pressure under which liquid phase polymerization or gas phase polymerization can be carried out at the above-

mentioned polymerization temperature. For example, a pressure in the range of from atmospheric pressure to about 100 kg/cm² is generally adopted, and a pressure in the range of from atmospheric pressure to about 50 kg/cm² is preferred. The polymerization time at the polymerization step is set so that the amount of the formed ultra-high-molecular-weight polyethylene is at least about 1000 g, preferably at least about 2000 g, per milligram-atom of titanium in the highly active titanium catalyst component. In order to form the ultra-high-molecular-weight polyethylene at the polymerization step, it is preferred that the polymerization reaction be carried out in the absence of hydrogen. After the polymerization reaction, the formed polymer can be once isolated in an inert medium atmosphere and stored.

As the inert medium that can be used at the polymerization step for formation of the ultra-high-molecular-weight polyethylene, there can be mentioned, for example, aliphatic hydrocarbons such as propane, butane, pentane, hexane, heptane, octane, decane and kerosene, alicyclic hydrocarbons such as cyclopentane and cyclohexane, aromatic hydrocarbons such as benzene, toluene and xylene, halogenated hydrocarbons such as dichloroethane, methylene chloride and chlorobenzene, and mixtures thereof. Use of an aliphatic hydrocarbon is especially preferred.

In the production of the olefin resin composition of the present invention, at the polymerization step other than the polymerization step for formation of the ultra-high-molecular-weight polyethylene, the polymerization reaction of the remaining olefin is carried out in the presence of hydrogen.

At the polymerization step other than the polymerization step for formation of the ultra-high-molecular-weight polyethylene, hydrogen is fed in an amount of 0.01 to 50 moles, preferably 0.05 to 30 moles, per mole of the olefin fed at this polymerization step.

At the polymerization step other than the polymerization step for formation of the ultra-high-molecular-weight polyethylene, it is preferred that the concentrations of the respective catalyst components in the polymerization reaction liquid in the polymerization vessel be such that the above-mentioned treated catalyst is contained in an amount of about 0.001 to about 0.1 milligram-atom, preferably about 0.005 to about 0.1 milligram-atom, as the titanium atom per liter of the polymerization liquid and the Al/Ti atomic ratio in the polymerization mixture is from about 1 to about 1000, preferably from about 2 to about 500. Accordingly, the organic aluminum compound catalyst component (B) can be additionally supplied for the above-mentioned purpose. In order to adjust the molecular weight and molecular weight distribution, hydrogen, an electron donor and a halogenated hydrocarbon can be made present in the polymerization reaction mixture.

The polymerization temperature is within a range where slurry polymerization or gas phase polymerization is possible. Namely, the polymerization temperature is at least about 40 °C, preferably about 50 to about 100 °C. A polymerization pressure of from atmospheric pressure to about 100 kg/cm², especially from atmospheric pressure to about 50 kg/cm², is recommended. The polymerization time is set so that the amount of the formed polymer is at least 1000 g, preferably at least about 5000 g, per milligram-atom of titanium in the titanium catalyst component.

In the above-mentioned process, polymerization to ultra-high-molecular-weight polyethylene is carried out at the first stage and polymerization to low-molecular-weight or high-molecular-weight polyethylene is carried out at the second and subsequent stages. It will be understood that this polymerization order can be reversed.

Fine Particulate Inorganic Filler

As the fine particulate inorganic filler (B) used in the present invention, there can be mentioned silicas such as dry method amorphous silica (Aerosil), wet method amorphous silica (white carbon), crystalline silica (cristobalite or quartz) and diatomaceous earth, aluminas such as α -alumina, aluminum hydroxide and alumina gel (gibbsite or boehmite), aluminum silicates such as synthetic aluminum silicate (amorphous) and natural aluminum silicate (kaolin or calcined kaolin), natural magnesium silicate (talc), synthetic magnesium silicate, synthetic basic magnesium silicate, natural and synthetic smectites clay minerals (bentonite and montmorillonite) synthetic aluminosilicates (zeolite), alkaline earth metal salts such as calcium carbonate, magnesium carbonate and barium sulfate, and magnesium oxide and magnesium hydroxide.

It is generally preferred that the fine particulate inorganic filler used in the present invention should have a median diameter of 0.1 to 30 μ m, particularly 0.5 to 10 μ m (Colter counter method).

The fine particulate inorganic filler is incorporated in the olefin resin composition in an amount of 1 to 70% by weight, preferably 5 to 50% by weight, especially preferably 10 to 30% by weight.

Fibrous Filler

Known fibrous fillers can be used as the fibrous filler (B) in the present invention without any limitation. For example, there can be mentioned a glass fiber, a carbon fiber, a boron fiber, a potassium titanate whisker, metal fibers such as a stainless steel fiber and an aluminum fiber, an aramid fiber, a polyester fiber and a polyamide fiber.

The fibrous filler has a fiber diameter of 1 to 50 μm , preferably 5 to 15 μm , and a fiber length of 1 to 10 mm, preferably 3 to 6 mm, and the aspect ratio is 200 to 10000, preferably 400 to 1200.

In the olefin resin composition of the present invention, the fibrous filler is incorporated in an amount of 1 to 70 parts by weight, preferably 3 to 50 parts by weight, especially preferably 5 to 30 parts by weight, per 100 parts by weight of the above-mentioned olefin resin composition (A) comprising the ultra-high-molecular-weight polyethylene and the low-molecular-weight or high-molecular-weight polyethylene. If the amount of the fibrous filler exceeds 70 parts by weight per 100 parts by weight of the olefin resin composition (A), the apparent melt viscosity increases and the injection moldability is degraded, and the weld strength of the molded article is degraded.

Liquid or Solid Lubricant

Petroleum type lubricating oils and synthetic lubricating oils can be used as the liquid lubricant (B) in the present invention. As the petroleum type lubricating oil, there can be used liquid paraffin, spindle oil, freezer oil, dynamo oil, turbine oil, machine oil and cylinder oil. As the synthetic lubricating oil, there can be used synthetic hydrocarbon oil, polyglycol oil, polyphenyl ether oil, ester oil, phosphoric acid ester oil, polychlorotrifluoroethylene oil, fluoroester oil, chlorinated biphenyl oil and silicone oil.

As the lubricating oil having a good compatibility with the olefin resin composition and being especially effective for improving the lubricating property, there can be mentioned a synthetic lubricating oil composed of an ethylene/ α -olefin copolymer having an ethylene content of 20 to 80 mole%, especially 30 to 70 mole%, and a number average molecular weight of 500 to 10000, especially 1000 to 5000. Propylene is preferred as the α -olefin component of this synthetic lubricating oil, but other α -olefins having up to 20 carbon atoms, especially up to 14 carbon atoms, can be used. It is preferred that the Q value (weight average molecular weight/number average molecular weight ratio) be up to 4, especially up to 3. This synthetic lubricating oil is characterized by a viscosity index of at least 120 and a dynamic viscosity of 10 to 2000 cst as measured at 100 °C. The structure, characteristics and preparation process of this synthetic lubricating oil are described in detail in Japanese Patent Application Laid-Open Specifications No. 117595/82 and No. 123205/82.

As the solid lubricant or sliding filler (B), there are mainly used graphite and molybdenum disulfide. Furthermore, there can be used boron nitride, tungsten disulfide, lead oxide, glass powder and metal soap. Still further, there can be used powders of fluorine resins such as a polytetrafluoroethylene resin (PTFE), an ethylene tetrafluoride/propylene hexafluoride copolymer resin (FEP), an ethylene tetrafluoride/perfluoroalkoxyethylene copolymer resin (PFA), a trifluorochloroethylene resin (PCTFE), an ethylene tetrafluoride/ethylene copolymer resin (ETFE) and a vinylidene fluoride resin, and other polymeric lubricant such as a polyphenylene sulfide resin powder. It is preferred that the sliding filler be used in the powdery form, and it also is preferred that the particle size be 1 to 100 μm , especially 10 to 50 μm .

The solid lubricant can be used singly or in combination with a liquid lubricant. For example, the lubricant can be incorporated in the form of, for example, a powder, a sol, a gel or a suspensoid in the olefin resin composition.

It is preferred that the liquid lubricant can be incorporated in an amount of 1 to 20% by weight, especially 2 to 5% by weight, based on the olefin resin composition. It is preferred that the solid lubricant be incorporated in an amount of 1 to 70 parts by weight, especially 3 to 50 parts by weight, particularly especially 5 to 30 parts by weight, per 100 parts by weight of the olefin resin composition (A).

Composition and Molding

In the present invention, the above-mentioned fine particulate inorganic filler, fibrous filler and liquid or solid lubricant can be used singly or in the form of a mixture thereof.

In the composition of the present invention, it is important that the above-mentioned additive should be dispersed in the olefin resin composition as finely and uniformly as possible. Fine dispersion can be accomplished by supplying the olefin resin composition and the additive to a single-screw or twin-screw extruding kneader and melt-kneading the mixture. Of course, known additives for olefin resins, such as an

antioxidant, a release agent and a pigment, can be incorporated at this mixing and kneading step according to a known recipe.

It is one of prominent advantages of the present invention that the so-formed composition can be molded by using a general-purpose injection molding machine. The injection molding conditions are not particularly critical. However, it is generally preferred that injection molding be carried out at a cylinder temperature of 200 to 290°C under an injection pressure of 1000 to 4000 kg/cm². Of course, injection molding can be carried out in one stage or a plurality of stages.

The composition of the present invention can be valuably used for various machine parts for which sliding characteristics are required, especially sliding parts, for example, various bearings, oilless bearings, joints, gears, cams, sliders, rollers, reels, cylinders, pistons and the like.

Since the composition of the present invention comprises, as a base material, a specific olefin resin composition comprising ultra-high-molecular-weight polyethylene and low-molecular-weight or high-molecular-weight polyethylene, the composition of the present invention can be molded into a machine part or the like at a high precision while retaining excellent characteristics inherently possessed by ultra-high-molecular-weight polyethylene. By incorporating a specific amount of a fine particulate inorganic filler into this olefin resin composition, the heat distortion temperature and flexural elastic modulus can be improved without substantial decrease of excellent characteristics of the olefin resin composition, such as a low wear coefficient, a low dynamic friction coefficient and a large critical PV value, and occurrence of "sink mark" and "warpage" can be prevented. Thus, the heat resistance, rigidity and moldability can be prominently improved.

In the case where a fibrous filler is incorporated in the olefin resin composition, the above-mentioned advantages can be similarly attained and, furthermore, the tensile strength and impact strength are highly improved.

Moreover, since the composition of the present invention comprises, as a base material, a specific olefin resin composition comprising ultra-high-molecular-weight polyethylene and low-molecular-weight or high-molecular-weight polyethylene, the composition of the present invention can be molded into a sliding part having a mechanical precision while retaining excellent self-lubricant property, abrasion resistance, impact strength inherently possessed by ultra-high-molecular-weight polyethylene and by incorporating a liquid or solid lubricant into this olefin resin composition, the dynamic friction coefficient and abrasion coefficient can be highly improved.

The present invention will now be described in detail with reference to the following examples that by no means limit the scope of the invention.

In the following examples, the physical properties were determined according to the following methods.

Tensile Test

The tensile test was carried out according to the method of ASTM D-638 by using a test piece of ASTM No. 4 at a tensile speed of 50 mm/min. The tensile strength (YS: kg/cm²) at yield, the tensile strength (TS: kg/cm²) at break and the elongation (EL: %) at break were determined.

Izod Impact Strength (kg·cm/cm)

The Izod impact strength was determined according to the method ASTM D-256 by using a notched test piece.

Olsen Rigidity (kg/cm²)

The Olsen rigidity was determined according to the method of ASTM D-747.

Flexural Strength (kg/cm²) and Flexural Elastic Modulus (kg/cm²)

The flexural strength and flexural elastic modulus were determined according to the method of ASTM D-790.

Heat Distortion Temperature (°C)

The heat distortion temperature was measured under a load of 4.64 kg/cm² by using a test piece having a size of 12.7 mm x 12.7 mm x 127 mm and a heat distortion tester (supplied by Toyo Seiki) according to

the method of ASTM D-648.

Dynamic Friction Coefficient

5 The dynamic friction test was carried out for 30 minutes under conditions of a compression load of 7.5 kg/cm² and a slip speed of 12 m/min by using a Matsubara type frictional abrasion tester (supplied by Toyo-Boldwin). The mating material was SUS 304 and the roughness of the sliding face was adjusted to 6s. An injection-molded rectangular plate having a size of 130 mm x 120 mm x 2 mm was used as the test piece.

10 Melting Critical PV Value (kg/cm²·m/min)

In a Matsubara type frictional abrasion tester (supplied by Toyo-Boldwin), the slip speed was adjusted to 12 m/min and the compression load was elevated from 2.5 kg/cm² to 25 kg/cm² stepwise at an interval of 15 2.5 kg/cm², and a resin was maintained for 30 minutes under each compression load and the PV value (load x speed) at which the resin was molten by heat of friction was measured. The mating material was SUS 304 and the roughness of the sliding face was adjusted to 6s. An injection-molded rectangular plate having a size of 130 mm x 120 mm x 2 mm was used as the test piece.

20 Frictional Abrasion Test

The frictional abrasion test was carried out for 168 hours under conditions of a compression load of 3.4 kg/cm² and a slip speed of 30 m/min by using a Matsubara type frictional abrasion tester (supplied by Toyo-Boldwin) and the abrasion coefficient (x 10⁻¹⁰ cm³/kg·m) was determined. The mating material was 25 SUS 304 and the roughness of the sliding face was adjusted to 6s. An injection-molded rectangular plate having a size of 130 mm x 120 mm x 2 mm was used as the test piece.

Molding Shrinkage (%)

30 The length and width of an injection-molded rectangular plate having a size of 130 mm x 120 mm x 2 mm were measured and the shrinkage of the molded article was determined based on the size of a mold according to the following formula:

35

$$\text{Shrinkage (\%)} = \frac{\left(\begin{array}{c} \text{size of} \\ \text{mold} \end{array} \right) - \left(\begin{array}{c} \text{size of} \\ \text{molded article} \end{array} \right)}{\text{size of mold}} \times 100$$

40

Intrinsic Viscosity [η]h of Low -Molecular-Weight or High-Molecular-Weight Polyethylene in Olefin Resin Composition

45 (1) The density du of the ultra-high-molecular-weight polyethylene and the density dc of the olefin resin composition were measured, and the density dh of the low-molecular-weight or high-molecular-weight polyethylene were determined according to the following formula:

50 $\frac{a}{d_u} + \frac{b}{d_h} = \frac{1}{d_c}$

wherein dh, dc and du are as defined above and a and b represent weight ratios of the ultra-high-molecular-weight polyethylene and the low-molecular-weight or high-molecular-weight polyethylene in the olefin resin composition, respectively.

55 (2) Various low-molecular-weight or high-molecular-weight polyethylene differing in the intrinsic viscosity were prepared under the same conditions (inclusive of the monomer composition and the catalyst) as adopted for the production of the low-molecular-weight or high-molecular-weight polyethylene, the density dh of which was measured, except that the hydrogen partial pressure was changed, and with

respect to the obtained polyethylenes, the relation between the intrinsic viscosity $[\eta]$ and the density was determined.

The density ρ , obtained in (1) above, of the low-molecular-weight or high-molecular-weight polyethylene was regarded as the density satisfying the so-determined relation, and the corresponding intrinsic viscosity $[\eta]_h$ was determined from this relation.

(3) The density of each sample was determined according to the following procedures. Two sets of laminates comprising an aluminum sheet (3 mm x 300 mm x 300 mm), an asbestos sheet (5 mm x 250 mm x 250 mm), a stainless steel sheet (3 mm x 220 mm x 220 mm) and a polyester film, which were piled in this order, were prepared. One set of the laminate was placed on a pressing face of a press molding machine so that the polyester film was located above, a molding flame (2mm x 200 mm x 200 mm) was placed on this plate, and the other laminate was placed on the molding frame so that the polyester film was located below.

The sample was charged in the molding frame and the sample was molten at $190 \pm 3^\circ\text{C}$ under a pressureless condition for 8 minutes and was then molded under a pressure of 300 kg/cm^2 for 5 minutes. Then, the sample was cooled to 60°C at a cooling speed of $15 \pm 2^\circ\text{C}$ and the sample was taken out. The sample was held in a thermostat oil tank maintained at $120 \pm 0.2^\circ\text{C}$ for 1 hour, and the sample was cooled to room temperature at a cooling speed of 1.5°C/min . Then, the sample was taken out and allowed to stand still at room temperature for 1 hour, and the density of the sample was measured according to the density gradient method (ASTM D-1505).

The following examples illustrate the preparation of the olefin resin composition.

Example A

(Preparation of Catalyst)

A homogeneous solution was prepared by heating and reacting 47.6 g (0.5 mole) of anhydrous magnesium chloride, 0.25 l of decalin and 0.23 l (1.5 moles) of 2-ethylhexyl alcohol at 130°C for 2 hours, and 7.4 ml (50 millimoles) of ethyl benzoate was added to the solution. The homogeneous solution was dropped with stirring into 1.5 l of TiCl_4 maintained at -5°C over a period of 1 hour. A separable glass flask having a capacity of 3 liters was used as the reaction vessel, and the stirring speed was adjusted to 950 rpm. After completion of the dropwise addition, the temperature was elevated to 90°C and reaction was carried out at 90°C for 2 hours. After termination of the reaction, the solid portion was collected by filtration and sufficiently washed with hexane to obtain a highly active, fine powdery titanium catalyst component. The catalyst component contained 3.8% by weight of the titanium atom.

(Polymerization)

Continuous polymerization was carried out by using a continuous two-staged polymerization apparatus comprising two polymerization tanks having an inner volume of 220 l, which were connected to each other in series. To the first-stage polymerization tank (hereinafter referred to as "polymerization tank 1") of the continuous two-stage polymerization apparatus was added 130 l of n-hexane, and the temperature was elevated to 40°C . Then, n-hexane at 35 l/hr, triethyl aluminum at 45 mM/hr, the titanium catalyst component at 1.0 milligram-atom/hr as the titanium atom and ethylene gas at $6.0 \text{ Nm}^3/\text{hr}$ were continuously introduced into the polymerization tank 1. The polymerization mixture slurry in the polymerization tank 1 was fed to the second-stage polymerization tank (hereinafter referred to as "polymerization tank 2") by means of a pump so that the volume of the reaction mixture was always 130 l. The polymerization pressure in the polymerization tank 1 was $4.8 \text{ kg/cm}^2\text{G}$.

In addition to the polymerization mixture slurry fed from the polymerization tank 1, n-hexane at 25 l/hr and ethylene gas at $18 \text{ Nm}^3/\text{hr}$ were continuously introduced into the polymerization tank 2. Hydrogen gas was appropriately introduced so that the ethylene/hydrogen molar ratio in the gas phase in the polymerization tank 2 was 1000/30. The slurry formed by the polymerization reaction was intermittently withdrawn from the bottom of the polymerization tank 2 by using a timer valve so that the level of the polymerization tank 2 was maintained at 120 l. The polymerization temperature in the polymerization tank 2 was 65°C , and the polymerization pressure was $4 \text{ kg/cm}^2\text{G}$. The obtained polymer was separated from the solvent by a centrifugal separator and dried in an N_2 current.

Then, $[\eta]$ and the content of each component of the obtained olefin resin composition, and $[\eta]$ and the melt torque T of the composition were measured according to the following methods.

The intrinsic viscosity $[\eta]$ was measured in decalin as the solvent at 135°C .

EP 0 315 481 B1

The melt torque T was expressed by the torque of the sample in the molten state, which was measured at a temperature of 240 °C under a pressure of 5 kg/cm² at an amplitude of ±3 ° and a vibration number of 6 cpm by using JSR Curastometer (supplied by Imanaka Kikai Kogyo).

It was found that the intrinsic viscosity $[\eta]_c$ of the olefin resin composition was 5.5 dl/g and the melt torque T of the olefin resin composition was 1.3 kg·cm.

Example B

(Preparation of Catalyst)

A homogeneous solution was prepared by heating and reacting 47.6 g (0.5 mole) of anhydrous magnesium chloride, 0.25 l of decalin and 0.23 l (1.5 moles) of 2-ethylhexyl alcohol at 130 °C for 2 hours, and 7.4 ml (50 millimoles) of ethyl benzoate was added to the solution. The homogeneous solution was dropped with stirring into 1.5 l of TiCl₄ maintained at -5 °C over a period of 1 hour. A separable glass flask having a capacity of 3 liters was used as the reaction vessel, and the stirring speed was adjusted to 950 rpm. After completion of the dropwise addition, the temperature was elevated to 90 °C and reaction was carried out 90 °C for 2 hours. After termination of the reaction, the solid portion was collected by filtration and sufficiently washed with hexane to obtain a highly active, fine powdery titanium catalyst component. The catalyst component contained 3.8% by weight of the titanium atom.

(Polymerization)

Continuous polymerization was carried out by using a continuous two-staged polymerization apparatus comprising two polymerization tanks having an inner volume of 220 l, which were connected to each other in series. To the first-stage polymerization tank (hereinafter referred to as "polymerization tank 1") of the continuous two-staged polymerization apparatus was added 130 l of n-hexane, and the temperature was elevated to 60 °C. Then, n-hexane at 35l/hr, triethyl aluminum at 45 mM/hr, the titanium catalyst component at 1.0 milligram-atom/hr as the titanium atom and ethylene gas at 4.3 Nm³/hr were continuously introduced into the polymerization tank 1. The polymerization mixture slurry in the polymerization tank 1 was fed to the second-stage polymerization tank (hereinafter referred to as "polymerization tank 2") by means of a pump so that the volume of the reaction mixture was always 130 l. The polymerization pressure in the polymerization tank 1 was 4.7 kg/cm²G.

In addition to the polymerization mixture slurry fed from the polymerization tank 1, n-hexane at 25 l/hr and ethylene gas at 11.2 Nm³/hr were continuously introduced into the polymerization tank 2. Hydrogen gas was appropriately introduced so that the ethylene/hydrogen molar ratio in the gas phase in the polymerization tank 2 was 1000/30. The slurry formed by the polymerization reaction was intermittently withdrawn from the bottom of the polymerization tank 2 by using a timer valve so that the level of the polymerization tank 2 was maintained at 120 l. The polymerization temperature in the polymerization tank 2 was 85 °C, and the polymerization pressure was 7.2 kg/cm²G. The obtained polymer was separated from the solvent by a centrifugal separator and dried in an N₂ current.

Then, $[\eta]$ and the content of each component of the obtained olefin resin composition, and $[\eta]$ and the melt torque T of the composition were measured according to the following methods.

The intrinsic viscosity $[\eta]$ was measured in decalin as the solvent 135 °C.

The melt torque T was expressed by the torque of the sample in the molten state, which was measured at a temperature of 240 °C under a pressure of 5 kg/cm² at an amplitude of 3 ° and a vibration number of 6 cpm by using JSR Curastometer (supplied by Imanaka Kikai Kogyo).

It was found that the intrinsic viscosity $[\eta]_c$ of the olefin resin composition was 5.4 dl/g and the melt torque T of the olefin resin composition was 1.4 kg·cm.

Example 1

Sample 1

By a Henschel mixer, 100 parts by weight of the olefin resin composition obtained in Example A, which had $[\eta]_c$ of 5.5 dl/g, a density of 0.968 g/cc and a melt torque T of 1.3 kg·cm was mixed with 10 parts by weight of talc having an average particle size of 1.75 μm (Hi-Filler #5000PJ supplied by Matsumura Sangyo) as the inorganic filler, and the mixture was pelletized by a single-screw extruder and various test pieces were formed by an injection molding machine (Model IS-50 supplied by Toshiba Kikai) under the

EP 0 315 481 B1

following conditions.

Injection Molding Conditions

5 Cylinder temperature (°C): 200/230/270/270
Injection pressure (kg/cm²): primary/secondary = 1200/800
Screw revolution (rpm): 97
Mold temperature (°C): 27 (water-cooled)
The obtained results are shown in Table 1.

10

Sample 2

The procedures for formation of sample 1 were repeated in the same manner except that the amount filled of talc was changed to 30 parts by weight.

15

Sample 3

The procedures for formation of sample 1 were repeated in the same manner except that the olefin resin composition (A) in which the filler was not incorporated was used.

20

Sample 4

The procedures for formation of sample 1 were repeated in the same manner except that the amount filled of talc was changed to 80 parts by weight and the mixture was pelletized by a twin-screw extruder.

25

Since the amount filled of talc was too large, the sliding characteristics were drastically degraded, and it was found that the composition was not suitable for practical use.

30

35

40

45

50

55

The obtained results are shown in Table 1.

Table 1

<u>Sample NO.</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>
Amount (parts by weight) of Filled Talc	10	30	0	80
Heat Distortion Temperature (°C) (4.64 kg/cm ²)	94	121	80	127
Flexural Elastic Modulus (kg/cm ²)	23000	33000	17000	40500
Dynamic Friction Coefficient	0.19	0.27	0.15	0.51
Melting Critical PV Value (kg/cm ² ·m/min)	420	330	450	120
Abrasion Coefficient (10 ⁻¹⁰ cm ³ /kg·m)	180	230	160	450
Shrinkage (%)	1.3	0.9	1.6	1.2
	1.2	0.9	1.5	1.0
length				
width				

Example 2

Sample 1

By a Henschel mixer, 100 parts by weight of the olefin resin composition obtained in Example A, which had $[\eta]$ c of 5.5 dl/g, a density of 0.968 g/cc and a melt torque T of 1.3 kg/cm was mixed with 2 parts by weight of an ethylene/ α -olefin copolymer synthetic oil having a molecular weight of 1300 and a dynamic viscosity of 100 cst as measured at 100°C (Lucant HC-100 supplied by Mitsui Petrochemical Industries, Ltd.) as the liquid lubricant, and the mixture was pelletized by a single-screw extruder, and a rectangular plate having a size of (130 mm x 120 mm x 2 mm) was formed by using an injection molding machine

EP 0 315 481 B1

(Model IS-50 supplied by Toshiba Kikai) under the following conditions and the plate was machined to prepare a test piece.

Injection Molding Conditions

- 5
Cylinder temperature ($^{\circ}\text{C}$): 200/230/270/270
Injection pressure (kg/cm^2): primary/secondary = 1000/800
Screw revolution (rpm): 97
Mold temperature ($^{\circ}\text{C}$): 27 (water-cooled)

10

Sample 2

The procedures for formation of sample 1 were repeated in the same manner except that the amount incorporated of the lubricating oil was changed to 10 parts by weight.

15

Sample 3

The procedures for formation of sample 1 were repeated in the same manner except that the amount incorporated of the lubricating oil was changed to 0.3 part by weight.

20

Since the amount of the lubricating oil was too small, no substantial improvement of the sliding characteristics was observed.

Sample 4

25

The procedures for formation of sample 1 were repeated in the same manner except that 2 parts by weight of graphite having a carbon content of 99.0%, an average particle size of $6\ \mu\text{m}$, a specific surface area of $15\ \text{N}_2\ \text{m}^2/\text{g}$ and a bulk density of $0.18\ \text{g}/\text{cc}$ (ACP#1000 supplied by Nippon Kokuen Kogyo) was used as the solid lubricant.

30 Sample 5

The procedures for formation of sample 4 were repeated in the same manner except that the amount incorporated of graphite was changed to 10 parts by weight.

35 Sample 6

The procedures for formation of sample 4 were repeated in the same manner except that the amount incorporated of graphite was changed to 0.3 part by weight.

40

Since the amount of the graphite was too small, no substantial improvement of the sliding characteristics was observed.

Example 7

45

The procedures for formation of sample 1 were repeated in the same manner except that the olefin resin composition A in which the lubricant was not incorporated was used.

50

55

The obtained results are shown in Table 2.

Table 2

<u>Sample No.</u>	<u>Flexural Strength (kg/cm²)</u>	<u>Flexural Modulus (kg/cm²)</u>	<u>Dynamic Friction Coefficient</u>	<u>Abrasion Coefficient (x10⁻¹⁰cm³/kg·cm)</u>
1	410	13000	0.12	150
2	340	9000	0.10	120
3	440	17000	0.15	160
4	450	16000	0.14	160
5	470	19000	0.12	200
6	450	17000	0.15	160
7	450	17000	0.15	160

Example 3

Sample 1

5 By a Henschel mixer, 100 parts by weight of the olefin resin composition obtained in Example B was mixed with 0.1 part of weight of tetrakis(methylene(3,5-di-tert-butyl-4-hydroxy)hydrocinnamate)methane (Irganox 1010 supplied by Nippon Ciba-Geigy) as the additive, 0.1 part by weight of tetrakis(2,4-di-tert-butylphenyl)-4,4-biphenylene diphosphite (Sandostab P-EPQ supplied Sandoz) as the additive, 0.12 part of weight of calcium stearate (supplied by Nippon Yushi) as the additive and 20 parts by weight of a glass fiber (CS6PE-921 supplied by Nitto Boseki) as the fibrous filler, and the mixture was supplied to a twin-screw extruder having an L/D ratio of 28 and a diameter of 45 mm and kneaded and granulated by passing the mixture through the extruder once at 220°C and 100 rpm. The formed pellet was molded into a rectangular plate having a size of 130 mm x 120 mm x 2 mm by using an injection molding machine (Model IS-50 supplied by Toshiba Kikai) under the following conditions. The molded plate was machined to form a test piece.

Injection Molding Conditions

20 Cylinder temperature (°C): 200/230/270/270
 Injection pressure (kg/cm²): primary/secondary = 1000/800
 Cycle (sec): primary/secondary/cooling = 5/3/25
 Injection speed: 2/10
 Screw revolution (rpm): 97
 Mold temperature (°C): 32 (water-cooled)
 25 The obtained results are shown in Table 3.

Samples 2 and 3

30 The procedures for formation of sample 1 were repeated in the same manner except that the amount used of the glass fiber was changed to 10 parts by weight or 30 parts by weight.
 The obtained results are shown in Table 3.

Sample 4

35 The procedures for formation of sample 1 were repeated in the same manner except that 20 parts by weight of a carbon fiber (Kureka Chop C-103 supplied by Kureha Kagaku Kogyo) was used as the fibrous filler.
 The obtained results are shown in Table 3.

40 Samples 5 and 6

The procedures for formation of sample 1 were repeated in the same manner except that the amount of the glass fiber was changed to 0 or 80 parts by weight.

45

50

55

The obtained results are shown in Table 3.

Table 3

Sample No.	1	2	3	4	5	6
olefin resin composition (%) (dl/g)	5.4	5.4	5.4	5.4	5.4	5.4
melt torque (kg·cm)	1.4	1.4	1.4	1.4	1.4	1.4
glass fiber (parts by weight)	20	10	30	—	—	80
carbon fiber (parts by weight)	—	—	—	20	—	—
tensile stress at yield (YS) (kg/cm ²)	—	—	—	—	330	↑ impossible
tensile strength at break (TS) (kg/cm ²)	660	550	940	740	170	—
elongation at break (EL) (%)	3	5	3	3	260	—
Izod impact strength (kg·cm/cm)	22.1	16.6	26.4	25.3	6	—
olsen rigidity (kg/cm ²)	16300	14000	21500	18000	11300	—
heat distortion temperature (°C) (18.6 kg/cm ²)	82	75	93	86	46	—
friction coefficient (μ)	0.22	0.19	0.31	0.25	0.15	—
abrasion loss (mg)	0.9	0.7	1.4	1.10	0.5	—

Example 4Sample 1

5 By a Henschel mixer, 100 parts by weight of the olefin resin composition obtained in Example B was mixed with 0.1 part of weight of tetrakis(methylene(3,5-di-tert-butyl-4-hydroxy)hydrocinnamate)methane (Irganox 1010 supplied by Nippon Ciba-Geigy) as the additive, 0.1 part by weight of tetrakis(2,4-di-tert-butylphenyl)-4,4-biphenylene diphosphite (Sandostab P-EPQ supplied by Sandoz) as the additive, 0.12 part by weight of calcium stearate (supplied by Nippon Yushi) as the additive and 10 parts by weight of a
10 graphite powder (CSP supplied by Nippon Kokuen Kogyo) as the sliding filler, and the mixture was supplied to a single-screw-extruder having an L/D ratio of 28 and a diameter of 25 mm and kneaded and granulated by passing the mixture through the extruder once at 190 °C and 50 rpm. The formed pellet was molded into a rectangular plate having a size of 130 mm x 120 mm x 2 mm by using an injection molding machine (Model IS-50 supplied by Toshiba Kikai) under the following conditions. The molded plate was machined to
15 form a test piece.

Injection Molding Conditions

Cylinder temperature (°C): 200/230/270/270
20 Injection pressure (kg/cm²): primary/secondary = 1000/800
Cycle (sec): primary/secondary/cooling = 5/3/25
Injection speed: 2/10
Screw revolution (rpm): 97
Mold temperature (°C): 32 (water-cooled)
25 The obtained results are shown in Table 4.

Sample 2

The procedures for formation of sample 1 were repeated in the same manner except that 10 parts by
30 weight of a powder of PTFE (Teflon TFE-T-TA-J supplied by Mitsui-Du Pont Fluorochemical) was used as the sliding filler.
The obtained results are shown in Table 4.

Samples 3 and 4

35 The procedures for formation of sample 1 were repeated in the same manner except that the amount of the graphite powder was changed to 0 or 80 parts by weight.

40

45

50

55

The obtained results are shown in Table 4.

Table 4

Sample No.	1	2	3	4
olefin resin composition (η) (dl/g)	5.4	5.4	5.4	5.4
melt torque (kg·cm)	1.4	1.4	1.4	1.4
sliding filler graphite powder (parts by weight)	10	—	—	80
PTFE powder (parts by weight)	—	10	—	—
tensile stress at yield (YS) (kg/cm ²)	240	210	330	—
tensile strength at break (TS) (kg/cm ²)	110	120	170	—
elongation at break (EL) (%)	90	120	260	—
Izod impact strength (kg·cm/cm)	7	4	6	—
olsen rigidity (kg/cm ²)	13000	9200	11300	—
friction (μ)	0.11	0.12	0.15	—
abrasion loss (mg)	0.3	0.7	0.5	—

injection molding impossible

The words IRGANOX, LUCANT and SANDOSTAB are Registered Trade Marks.

Claims

1. A olefin resin composition for injection molding, which comprises (A) an olefin resin composition comprising ultra-high-molecular-weight polyethylene having an intrinsic viscosity of 10 to 40 dl/g as measured in decalin as the solvent at 135°C and low-molecular-weight or high-molecular-weight polyethylene having an intrinsic viscosity lower than that of the ultra-high-molecular-weight polyethylene, in which the ultra-high-molecular-weight polyethylene is present in an amount of 15 to 40% by weight based on the sum of both the polyethylenes and the two polyethylenes as a whole have an intrinsic viscosity $[\eta]_C$ of 3.5 to 15 dl/g and a melt torque T lower than 4.5 kg cm as measured at 240°C under a pressure of 5 kg.cm² at an amplitude of $\pm 3^\circ$ and a frequency of 360 Hz (6 cpm), and

EP 0 315 481 B1

(B) 1 to 70% by weight, based on the olefin resin composition, of an additive selected from fine particulate inorganic fillers, fibrous fillers and liquid and solid lubricants.

- 5 2. A composition according to claim 1, wherein the low-molecular-weight or high-molecular-weight polyethylene in the olefin resin composition (A) has an intrinsic viscosity $[\eta]_h$ of 0.1 to 5 dl/g.
3. A composition according to claim 1 or claim 2, wherein the ultra-high-molecular-weight polyethylene is present in an amount of 20 to 35% by weight in the olefin resin composition (A).
- 10 4. A composition according to any one of claims 1 to 3 comprising a fine particulate inorganic filler having a median diameter of 0.1 to 30 μm .
5. A composition according to any one of claims 1 to 4 comprising talc as the fine particulate inorganic filler (B).
- 15 6. A composition according to any one of claims 1 to 5 comprising a fine particulate inorganic filler in an amount of 5 to 50% by weight.
7. A composition according to any one of claims 1 to 6 comprising an inorganic or organic fibrous filler having a fiber diameter of 1 to 50 μm and a fiber length of 1 to 10 μm .
- 20 8. A composition according to any one of claims 1 to 7 comprising glass fiber or carbon fiber as fibrous filler.
- 25 9. A composition according to any one of claims 1 to 8 comprising a fibrous filler in an amount of 3 to 50% by weight.
10. A composition according to any one of claims 1 to 9 comprising a petroleum type lubricating oil or synthetic lubricating oil as liquid lubricant.
- 30 11. A composition according to any one of claims 1 to 10 comprising a synthetic lubricating oil composed of an ethylene/ α -olefin copolymer having an ethylene content of 20 to 80 mole% and a number average molecular weight of 500 to 10000 as liquid lubricant.
- 35 12. A composition according to any one of claims 1 to 11 comprising a liquid lubricant in an amount of 1 to 20% by weight.
13. A composition according to any one of claims 1 to 12 comprising a powder having a particle size of 1 to 100 μm as solid lubricant.
- 40 14. A composition according to any one of claims 1 to 13 comprising a powder of graphite or polytetrafluoroethylene as solid lubricant.
15. A composition according to any one of claims 1 to 14 comprising a solid lubricant in an amount of 3 to 50% by weight.
- 45 16. A molded article formed by injection-molding a composition according to any one of claims 1 to 15.
- 50 17. A molded article according to claim 16 formed by injection molding the composition at a cylinder temperature of 200 to 290 °C under an injection pressure of 1000 to 4000 kg/cm².
- 55 18. A sliding material which comprises an olefin resin composition comprising ultra-high-molecular-weight polyethylene having an intrinsic viscosity of 10 to 40 dl/g as measured in decalin as the solvent at 135 °C and low-molecular-weight or high-molecular-weight polyethylene having an intrinsic viscosity lower than that of the ultra-high-molecular-weight polyethylene, in which the ultra-high-molecular-weight polyethylene is present in an amount of 15 to 40% by weight based on the sum of both of the polyethylenes and the two polyethylenes as a whole have an intrinsic viscosity $[\eta]_c$ of 3.5 to 15 dl/g and a melt torque T lower than 4.5 kg cm, and 1 to 70% by weight, based on the olefin resin

composition, of a liquid or solid lubricant.

Patentansprüche

- 5 1. Olefinharzzusammensetzung zum Spritzgießen, welche (A) eine Olefinharzzusammensetzung, umfassend Polyethylen mit sehr hohem Molekulargewicht und einer in Dekalin als Lösungsmittel bei 135 °C gemessenen Grenzviskosität von 10 bis 40 dl/g und Polyethylen mit geringem Molekulargewicht oder hohem Molekulargewicht, das eine niedrigere Grenzviskosität besitzt als das Polyethylen sehr hohen Molekulargewichts, in welcher das Polyethylen sehr hohen Molekulargewichts in einer auf die Summe
10 beider Polyethylene bezogenen Menge von 15 bis 40 Gew.-% vorliegt und die zwei Polyethylene als Ganzes eine Grenzviskosität $[\eta]_c$ von 3,5 bis 15 dl/g und ein Drehmoment in der Schmelze (T) von weniger als 4,5 kg * cm, gemessen bei 240 °C unter einem Druck von 5 kg/cm² bei einer Amplitude von $\pm 3^\circ$ und einer Frequenz von 360 Hz (6 cpm), aufweisen, und (B) 1 bis 70 Gew.-%, bezogen auf die Olefinharzzusammensetzung, eines aus feinen teilchenförmigen anorganischen Füllstoffen, faserförmigen Füllstoffen und flüssigen sowie festen Gleitstoffen gewählten Zusatzstoffes, umfaßt.
- 15 2. Zusammensetzung gemäß Anspruch 1, wobei das Polyethylen mit geringem Molekulargewicht oder hohem Molekulargewicht in der Olefinharzzusammensetzung (A) eine Grenzviskosität $[\eta]_h$ von 0,1 bis 5 dl/g aufweist.
- 20 3. Zusammensetzung gemäß Anspruch 1 oder Anspruch 2, wobei das Polyethylen mit sehr hohem Molekulargewicht in einer Menge von 20 bis 35 Gew.-% in der Olefinharzzusammensetzung (A) vorliegt.
- 25 4. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 3, umfassend einen feinen, teilchenförmigen, anorganischen Füllstoff mit einem mittleren Durchmesser von 0,1 bis 30 μm .
- 30 5. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 4, umfassend Talk als feinen, teilchenförmigen, anorganischen Füllstoff (B).
- 35 6. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 5, umfassend einen feinen teilchenförmigen anorganischen Füllstoff in einer Menge von 5 bis 50 Gew.-%.
- 40 7. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 6, umfassend einen anorganischen oder organischen faserförmigen Füllstoff mit einem Faserdurchmesser von 1 bis 50 μm und einer Faserlänge von 1 bis 10 μm .
- 45 8. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 7, umfassend Glasfaser oder Kohlefaser als faserförmiger Füllstoff.
- 50 9. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 8, umfassend einen faserförmigen Füllstoff in einer Menge von 3 bis 50 Gew.-%.
- 55 10. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 9, umfassend ein Schmieröl vom Petroleum-Typ oder ein synthetisches Schmieröl als flüssiges Gleitmittel.
11. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 10, umfassend ein synthetisches Schmieröl, das aus einem Ethylen/ α -Olefin-Copolymer mit einem Ethylengehalt von 20 bis 80 Mol-% und einem zahlenmittleren Molekulargewicht von 500 bis 10000 besteht, als flüssiges Gleitmittel.
12. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 11, umfassend ein flüssiges Gleitmittel in einer Menge von 1 bis 20 Gew.-%.
13. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 12, umfassend ein Pulver mit einer Teilchengröße von 1 bis 100 μm als festes Gleitmittel.
14. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 13, umfassend ein Pulver aus Graphit oder Polytetrafluorethylen als festes Gleitmittel.

EP 0 315 481 B1

15. Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 14, umfassend ein festes Gleitmittel in einer Menge von 3 bis 50 Gew.-%.
16. Geformter Gegenstand, gebildet durch Spritzgießen einer Zusammensetzung gemäß mindestens einem der Ansprüche 1 bis 15.
17. Geformter Gegenstand gemäß Anspruch 16, gebildet durch Spritzgießen der Zusammensetzung bei einer Zylindertemperatur von 200 bis 290 °C und einem Spritzdruck von 1000 bis 4000 kg/cm².
18. Gleitmaterial, welches eine Olefinharzzusammensetzung, umfassend Polyethylen mit sehr hohem Molekulargewicht und einer in Dekalin als Lösungsmittel bei 135 °C gemessenen Grenzviskosität von 10 bis 40 dl/g und Polyethylen mit geringem Molekulargewicht oder hohem Molekulargewicht, das eine niedrigere Grenzviskosität besitzt als das Polyethylen sehr hohen Molekulargewichts, in welchem das Polyethylen sehr hohen Molekulargewichts in einer auf die Summe beider Polyethylene bezogenen Menge von 15 bis 40 Gew.-% vorliegt und die zwei Polyethylene als Ganzes eine Grenzviskosität $[\eta]_c$ von 3,5 bis 15 dl/g und ein Drehmoment in der Schmelze (T) von weniger als 4,5 kg * cm aufweisen, und 1 bis 70 Gew.-% eines flüssigen oder festen Gleitstoffes, bezogen auf die Olefinharzzusammensetzung, umfaßt.

Revendications

1. Composition de résine oléfinique pour le moulage par injection, qui comprend :
- (A) une composition de résine oléfinique comprenant un polyéthylène de poids moléculaire très élevé ayant une viscosité intrinsèque de 10 à 40 dl/g mesurée dans la décaline comme solvant à 135 °C et un polyéthylène de poids moléculaire faible ou élevé ayant une viscosité intrinsèque inférieure à celle du polyéthylène de poids moléculaire très élevé, dans laquelle le polyéthylène de poids moléculaire très élevé est présent en une quantité de 15 à 40% en poids sur base de la somme des deux polyéthylènes et les deux polyéthylènes ensemble ont une viscosité intrinsèque $[\eta]_c$ de 3,5 à 15 dl/g et un couple de torsion à l'état fondu inférieur à 4,5 kg.cm mesuré à 240 °C sous une pression de 5 kg.cm² à une amplitude de $\pm 3^\circ$ et à une fréquence de 360 Hz (6 cpm), et (B) 1 à 70% en poids, sur base de la composition de résine oléfinique, d'un additif choisi parmi les charges inorganiques particulaires fines, les charges fibreuses et les lubrifiants liquides et solides.
2. Composition suivant la revendication 1, dans laquelle le polyéthylène de poids moléculaire faible ou élevé dans la composition de résine oléfinique (A) a une viscosité intrinsèque $[\eta]_h$ de 0,1 à 5 dl/g.
3. Composition suivant la revendication 1 ou la revendication 2, dans laquelle le polyéthylène de poids moléculaire très élevé est présent en une quantité de 20 à 35% en poids de la composition de résine oléfinique (A).
4. Composition suivant l'une quelconque des revendications 1 à 3, comprenant une charge inorganique particulaire fine ayant un diamètre médian de 0,1 à 30 μm .
5. Composition suivant l'une quelconque des revendications 1 à 4, comprenant du talc comme charge inorganique particulaire fine (B).
6. Composition suivant l'une quelconque des revendications 1 à 5, comprenant une charge inorganique particulaire fine en une quantité de 5 à 50% en poids.
7. Composition suivant l'une quelconque des revendications 1 à 6, comprenant une charge fibreuse inorganique ou organique ayant un diamètre de fibre de 1 à 50 μm et une longueur de fibre de 1 à 10 μm .
8. Composition suivant l'une quelconque des revendications 1 à 7, comprenant de la fibre de verre ou de la fibre de carbone comme charge fibreuse.
9. Composition suivant l'une quelconque des revendications 1 à 8, comprenant une charge fibreuse en une quantité de 3 à 50% en poids.

10. Composition suivant l'une quelconque des revendications 1 à 9, comprenant une huile de lubrification de type pétrole ou une huile de lubrification synthétique comme lubrifiant liquide.
- 5 11. Composition suivant l'une quelconque des revendications 1 à 10, comprenant une huile de lubrification synthétique composée d'un copolymère éthylène/ α -oléfine ayant une teneur en éthylène de 20 à 80 moles% et un poids moléculaire moyen de 500 à 10 000 comme lubrifiant liquide.
12. Composition suivant l'une quelconque des revendications 1 à 11, comprenant un lubrifiant liquide en une quantité de 1 à 20% en poids.
- 10 13. Composition suivant l'une quelconque des revendications 1 à 12, comprenant une poudre ayant une granulométrie de 1 à 100 μ m comme lubrifiant solide.
14. Composition suivant l'une quelconque des revendications 1 à 13, comprenant une poudre de graphite ou de polytétrafluoroéthylène comme lubrifiant solide.
- 15 15. Composition suivant l'une quelconque des revendications 1 à 14, comprenant un lubrifiant solide en une quantité de 3 à 50% en poids.
- 20 16. Article moulé formé par moulage par injection d'une composition suivant l'une quelconque des revendications 1 à 15.
17. Article moulé suivant la revendication 16, formé par moulage par injection de la composition à une température de matrice de 200 à 290 °C sous une pression d'injection de 1000 à 4000 kg/cm².
- 25 18. Matière glissante qui comprend une composition de résine oléfinique comprenant un polyéthylène de poids moléculaire très élevé ayant une viscosité intrinsèque de 10 à 40 dl/g mesurée dans la décaline comme solvant à 135 °C et un polyéthylène de poids moléculaire faible ou élevé ayant une viscosité intrinsèque inférieure à celle du polyéthylène de poids moléculaire très élevé, dans laquelle le polyéthylène de poids moléculaire très élevé est présent en une quantité de 15 à 40% en poids sur base de la somme des deux polyéthylènes et les deux polyéthylènes ensemble ont une viscosité intrinsèque [η]cd₃ 3,5 à 15 dl/g et un couple de torsion à l'état fondu inférieur à 4,5 kg.cm, et 1 à 70% en poids, sur base de la composition de résine oléfinique, d'un lubrifiant liquide ou solide.
- 30
- 35
- 40
- 45
- 50
- 55

THIS PAGE BLANK (USPTO)